TECHNICAL DATA SHEET

40 GLAMOUR URETHANE CLEARCOAT 4.2 VOC

TECHNICAL CALLS: 1-800-321-0672

Product Numbers:

40 (Activators: **42, 43, 44**)



DESCRIPTION:

U.S. Chemical & Plastics' 40 Glamour Urethane Clearcoat is a versatile high performance 2-coat 4.2 VOC urethane clearcoat designed to provide a deep, glossy glamour finish. Use in spot, panel, multi-panel and overall refinishing. USC's 40 Glamour Urethane Clearcoat delivers excellent flow, leveling and UV resistance with high gloss and DOI.



MIX RATIO: 4:1

Combine components by volume. Mix thoroughly and strain before using.

- 4 Parts USC 40 Glamour Urethane Clearcoat 4.2 VOC
- 1 Part USC 42 Fast, 43 Medium or 44 Slow Activator



POT LIFE:

> 5 Hours (@ 78° F / 25.6° C)



SURFACE PREPARATION:

Make repairs as needed. Mask vehicle to protect from overspray. Apply basecoat color to repair area and allow to dry according to paint manufacturer's recommendations.





GUN SET UP:

Conventional: 1.3mm – 1.5mm HVLP: 1.3mm – 1.4mm



AIR PRESSURE:

Conventional: 50 – 55 psi at the gun HVLP: 8 – 10 psi at the cap



APPLICATION:

2 medium wet coats



FLASH TIME:

8 – 10 minutes in between coats (@ 72° F / 22° C)



DRY TIME TO BUFF:

18 – 24 hours (@ 72° F / 22° C) Bake: 30 minutes @ 140° F / 60° C)

Excessive film build and cool temperatures will extend dry times.



PHYSICAL PROPERTIES: (Ready To Spray)

VOC: 4.2 lbs./gallon Theoretical Coverage: 610 sq. ft. @ 1.0 mil Weight Solids: 45.0% Volume Solids: 38.2% Recommended Dried Film Thickness: 2.0 mils



HEALTH & SAFETY:

Read all warnings, first aid and safety for all components before using. Keep out of reach of children and animals. Wear a properly fitting NIOSH/MSHA approved respirator. Select positive pressure supplied respirator (TC-19C or equivalent) for isocyanates. Follow the respirator manufacturer's directions for use. Protect hands with impervious rubber gloves. Wear face, skin and eye protection. USC products are for industrial use by professional, trained painters.